

AMARULA POL RECT 60X120

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A037989 60x120 8,80 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality

UNE-EN 14411

It accomplished all requeriments

| PHYSICAL PROPERTIES | | | | |
|--------------------------------------|-----------------|-----------------------|--|--|
| | | | | |
| Water absorption capacity | EN ISO 10545-03 | < 0,5% | | |
| Flexion resistance | EN ISO 10545-04 | $=>40 \text{ N/mm}^2$ | | |
| Abrasion resistance (glazed Ceramic) | EN ISO10545-07 | III | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | |
| Frost resistance | EN ISO 10545-12 | It stands the test | | |

| CHEMICAL PROPERTIES | | | | |
|--|-----------------|-----|--|--|
| Resistance to acids | EN ISO 10545-13 | GLA | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | |
| Stains resistance | EN ISO 10545-14 | 5 | | |









MIRROR AMARULA A POL RECT 60X120

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A038958 60x120 9,70 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality

UNE-EN 14411

It accomplished all requeriments

| PHYSICAL PROPERTIES | | | | |
|--------------------------------------|-----------------|------------------------------------|--|--|
| Water absorption capacity | EN ISO 10545-03 | < 0,5% | | |
| Flexion resistance | EN ISO 10545-04 | \Rightarrow 40 N/mm ² | | |
| Abrasion resistance (glazed Ceramic) | EN ISO10545-07 | III | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | |
| Frost resistance | EN ISO 10545-12 | It stands the test | | |

| CHEMICAL PROPERTIES | | | | |
|---------------------|---|--|--|--|
| EN ISO 10545-13 | GLA | | | |
| EN ISO 10545-13 | GLA | | | |
| EN ISO 10545-13 | GA | | | |
| EN ISO 10545-13 | GA | | | |
| EN ISO 10545-14 | 5 | | | |
| | EN ISO 10545-13 EN ISO 10545-13 EN ISO 10545-13 | | | |









MIRROR AMARULA B POL RECT 60X120

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A038959 60x120 9,70 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality

UNE-EN 14411

It accomplished all requeriments

| PHYSICAL PROPERTIES | | | | |
|--------------------------------------|-----------------|-----------------------|--|--|
| Water absorption capacity | EN ISO 10545-03 | < 0,5% | | |
| Flexion resistance | EN ISO 10545-04 | $=>40 \text{ N/mm}^2$ | | |
| Abrasion resistance (glazed Ceramic) | EN ISO10545-07 | III | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | |
| Frost resistance | EN ISO 10545-12 | It stands the test | | |

| CHEMICAL PROPERTIES | | | | |
|---------------------|---|--|--|--|
| EN ISO 10545-13 | GLA | | | |
| EN ISO 10545-13 | GLA | | | |
| EN ISO 10545-13 | GA | | | |
| EN ISO 10545-13 | GA | | | |
| EN ISO 10545-14 | 5 | | | |
| | EN ISO 10545-13 EN ISO 10545-13 EN ISO 10545-13 EN ISO 10545-13 | | | |










LAVABO DE PIE ROMA

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040867 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO NISO DCHA.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040866 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO NISO IZQ.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040865 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO AXEL CEN.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040870 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO AXEL DCHA.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040869 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO AXEL IZQ.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040868 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO AXEL DOBLE 160

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040871 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO ENEA CEN.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040874 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO ENEA DCHA.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040873 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO ENEA IZQ.

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040872 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test










LAVABO ENEA DOBLE 160

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A040875 0,00 PC BIA GL



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 It stands the test





